







98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-43-211-6144 FAX 82-43-211-6148

Report No: TAK-2020-115673Representative: YOO JUNG SEUKCompany name: HYUNDAI L&CAddress: 1077, Cheonho-daero, Gangdong-gu, Seoul, Republic of Korea

Receipt Date : 2020.07.24. Test Completion Date : 2020.08.07.

Sample name : HANEX SOLID SURFACES

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD	SITE
Compressive Strength(**)	MPa	-	118	ISO 604 : 2002	AK

** Specimen: Type B, Speed of Testing: 1 mm/min

- AK: 98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea
- Usage of Report : QUALITY CONTROL
- Note: 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 - 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 - 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

The above testing certificate is the accredited test result by Korea Laboratory Accreditation Scheme, which signed the ILAC-MRA.

Baek, Yeong Min

Prepared by Baek, Yeong Min Tel : 02-2092-3706

You Seok

Reviewed by You Seok Tel: 1577-0091(ARS ①→④)

2020.08.07

Korea Testing & Research Institute

Accredited by KOLAS, Republic of KOREA

President Know Oh-jung



QR Code for forgery

Page: 1 of 1



A4(210 X 297)

전자문서본(Electronic Copy)