

TEST REPORT

40, Yeongudanji-ro, Ochang-eup, Cheongwon-gun, Chungcheongbuk-do,
363-883 Rep. of KOREA

TEL 82-43-211-6144 FAX 82-43-211-6148

Report No : TAC-003235

Receipt Date : Jul.24.2015

Client : HAN MYEUNG HO

Test Completion Date : Aug.06.2015

Hanwha L&C

7_8F, CENTER1 Bldg, 26, Uljiro 5-gil, Jung-gu, Seoul, Korea

Sample : Scagliola(HANEX) D-2

TEST RESULTS

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) °C)	-	-	1.760	ASTM D792-13(Method A)
Rockwell Hardness(HRM)	-	-	88	ASTM D785-08(Procedure A)
Tensile Strength	MPa	-	39.4	ASTM D638-14(*)
Tensile Modulus of Elasticity	GPa	-	10.8	ASTM D638-10(*)
Flexural Strength	MPa	-	65.2	ASTM D790-10(**)
Flexural Modulus of Elasticity	GPa	-	10.3	ASTM D790-10(**)
Izod Impact Strength	J/m	-	17	ASTM D256-10(Method A)
Water Absorption(24 h Immersion)	%	-	0.02	ASTM D570-98(2010)e1
Density(23 °C)	g/cm ³	-	1.755	ASTM D792-13(Method A)
Heat Resistance Test	-	-	No Defects	JIS K 6902 : 2008
Hot Water Resistance Test	-	-	No Defects	JIS K 6902 : 2008
Deflection Temperature Under Load(1.82 MPa)	°C	-	111	ASTM D648-07(Method B)
Thermal Expansion	1/°C	-	2.6 × 10 ⁻⁴	JIS K 6911 : 2006

* Specimen: Type I, Speed of Testing: 5 mm/min(Modulus: 1 mm/min)

** Speed of Testing: 5.1 mm/min, Support Span: 190 mm

- Next Page -

Cho Hyeong-gil

Prepared by Cho Hyeong-gil
E-mail: gil@ktr.or.kr

You Seok

Reviewed by You Seok
Technical Manager
Tel: 1577-0091(ARS ①→④)

Aug.06.2015

Korea Testing & Research Institute

President



QR Code to verify genuineness

TEST REPORT

40, Yeongudanji-ro, Ochang-eup, Cheongwon-gun, Chungcheongbuk-do,
363-883 Rep. of KOREA

TEL 82-43-211-6144 FAX 82-43-211-6148

Report No : TAC-003235

Receipt Date : Jul.24.2015

Client : HAN MYEUNG HO

Test Completion Date : Aug.06.2015

Hanwha L&C

7_8F, CENTER1 Bldg, 26, Uljiro 5-gil, Jung-gu, Seoul, Korea

Sample : Scagliola(HANEX) D-2

TEST RESULTS

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

* USAGE : QUALITY CONTROL

NOTE : 1. The test results on this test report are only limited to the samples and sample names provided by the customer and KTR does not guarantee the quality of all products of the customer, and you can confirm the authenticity of the test report online (www.ktr.or.kr) or by using the QR code.
2. This test report shall not be used for public relation, advertisement, lawsuit and any other purposes outside the scope of its defined usage.
3. Only original copy (including certified copy) of the test report is valid – electronic copy (hard and/or soft) is for your reference only.

Cho Hyeong-gil

Prepared by Cho Hyeong-gil
E-mail: gil@ktr.or.kr

You Seok

Reviewed by You Seok
Technical Manager
Tel: 1577-0091(ARS ①→④)

Aug.06.2015

Korea Testing & Research Institute

President



QR Code to verify genuineness

2 of Total 2 Page(s)

Electronic copy is for your reference only.

전자문서본(Electronic Copy)