



TEST REPORT

1. NO : CT17-040731

2. Client

○ Name : Hanwha L & C Corporation

○ Address : 7_8F, CENTER1 Bldg, 26, Uljiro 5-gil, Jung-gu, Seoul, Korea

3. Date of Test : 2017.03.27 ~ 2017.04.25

4. Use of Report : Quality Control



5. Test Sample : BODAQ-Plate

6. Test Method

(1) ASTM G 21-15

Reissuance(R1)

Date : 2017.06.15

Affirmation	Tested By		Technical Manager	
	Name : Jong Yoon Son		Name : Hoo Seok Lee	
Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the qualities of the lot from which the sample was taken or of apparently identical or similar products.				

2017.04.25

Korea Conformity Laboratories

President Kyung Sik Kim



Address : 28116 40, Yeongudangi-ro, Ohchang-Eup, Cheongwon-Gu, Cheongju-si, Chungbuk, Korea 82-43-234-8747

Result Inquiry : Chungbuk Branch 82-43-718-9056

TEST REPORT

No : CT17-040731


7. Test Results

Test Items	Unit	Test Results				Test method	Testing Environment
		Test period of incubation					
		After 1 week	After 2 weeks	After 3 weeks	After 4 weeks		
Fungal resistance test	Grade	0	0	0	0	ASTM G 21-15	(29.0 ± 0.2) °C (93.6 ± 2.0) % R.H.

※ Name of Used Fungi(Mixed Fungi)
Aspergillus brasiliensis ATCC 9642
Penicillium funiculosum ATCC 11797
Chaetomium globosum ATCC 6205
Trichoderma virens ATCC 9645
Aureobasidium pullulans ATCC 15233

※ Assessment of Results

- 0 : None
- 1 : Traces of growth (less than 10 %)
- 2 : Light growth (10 to 30 %)
- 3 : Medium growth (30 to 60 %)
- 4 : Heavy growth (60 % to complete coverage)



<Picture 1. BODAQ-Plate (after 4 weeks)>

----- End of Report -----